

Shrinkage

Roving samples were held at each temperature for fifteen hours. After that time they were measured for shrinkage. All fiber compositions showed less than three percent shrinkage after fifteen hours at 2372°F (1300°C). Fiber compositions other than Nextel™ Roving 312 showed shrinkage of less than 1.5% at these conditions.

**% Shrinkage vs Temperature
(15 hours)**

